











Malaya ARD Gray Porcelain Floor-Wall Tile

Referencia/Reference: 564242501
Formato/Format: 11X22 in.
Color: Gris/Gray



	TRÁFICO TRAFFIC	Comercial Moderado / Moderate Commercial
	ACABADO FINISH	Mate / Matte
	ASPECTO APPEARANCE	Caras Diferenciadas / Differentiated Faces
	M2 POR CAJA SQ.FT APPROX	1,6 17,6
	UNIDADES PIECES	10
	PESO BRUTO CAJA kg WEIGHT LB APPROX	29,44 64,7
	ESPESOR NOMINAL NOMINAL THICKNESS	8,6 ± 0,2
	CAJAS POR ESTIBA CARTONS PER PALLET	60
	VOLATILE ORGANIC COMPOUNDS	0

El color presentado en la fotografía es una aproximación al color real.
The color represented in the photograph is an approximation to the real color.

Floors for use in commercial areas without direct access from the street, such as: offices, consulting rooms, rooms in general, fixed points and common areas of residential buildings. For matte finish floors traffic should be less than 500 people per day on average and for glossy finish floors traffic should be less than 200 people per day on average. These floors are also suitable for all residential areas. Important: Do not use in commercial areas such as supermarkets and hypermarkets, industries, public offices, corridors and common areas of shopping malls.

Caution: With the exception of Corona ARD® products, ceramic products decrease their slip resistance when in contact with water. In humid areas, products with a high coefficient of friction are recommended.

CHARACTERISTICS, ADVANTAGES AND BENEFITS:

The Malaya Slip Resistance Gray Porcelain Tile in matte finish and a 11X22 in. format, with a design inspired by a mixture of Sandstone and Basalt stones of very smooth grain, which provides high combinability to the environments. Ideal for moderate commercial use. It has ARD® technology Slip Resistance Technology, high friction texture, ideal for installation in areas with high risk of slipping. This type of finish requires a greater effort in cleaning the floor, due to the exposure of the product to elements such as dust, humidity, among others. It has three (3) differentiated faces, with subtle differences between one piece and another to give greater realism and naturalness to the product. Ultra-resistant to shocks, scratches, stains and humidity, it also has Digital Printing technology (HIGH DEFINITION HD).

Garantía Corona | Corona quality guaranteed: 12 Años/Years

Orchid Ceramics
by **corona**

Malaya ARD Gray Porcelain Floor-Wall Tile

CARACTERÍSTICAS TÉCNICAS TECHNICAL CHARACTERISTICS		ENSAYO TEST	ESPECIFICACIÓN SPECIFICACION NTC 919 / ISO 13006	MEDICIONES LOTES PROMEDIO CORONA/ CORONA AVERAGE LOT MEASUREMENTS
ANCHO Y LARGO LENGTH AND WIDTH		NTC 4321 - 2 ISO 10545 - 2	(±) 2.00% del tamaño de fabricación; hasta máximo 5 mm	(±) 2.00% del tamaño de fabricación; hasta máximo 5 mm
PLANIRADIDAD DE LA SUPERFICIE SURFACE FLATNESS	Curvatura Central Central Curvature	NTC 4321 - 2 ISO 10545 - 2	(±) 0.50% de la diagonal del tamaño de fabricación	(±) 0.30% de la diagonal del tamaño de fabricación
	Curvatura del lado Edge Curvature	NTC 4321 - 2 ISO 10545 - 2	(±) 0.50% relativa al correspondiente tamaño de fabricación	(±) 0.30% relativa al correspondiente tamaño de fabricación
	Ortogonalidad Warpage	NTC 4321 - 2 ISO 10545 - 2	(±) 0.50% de la diagonal del tamaño de fabricación	(±) 0.30% de la diagonal del tamaño de fabricación
DEFECTOS SUPERFICIALES SURFACE DEFECTS		NTC 4321 - 2 ISO 10545 - 2	Mínimo 95% libre de defectos/ Minimum 95% without defects	Mínimo 95% libre de defectos/ Minimum 95% without defects
ABSORCIÓN DE AGUA WATER ABSORPTION		NTC 4321 - 3 ISO 10545 - 3	Máximo 0.50%	Máximo 0.50%
RESISTENCIA A LA ROTURA BREAKING STRENGTH		NTC 4321 - 4 ISO 10545 - 4	Mínimo 1300 N / Minimum 1300 N	Mínimo 1400 N / Minimum 1400 N
MÓDULO DE ROTURA MODULUS OF RUPTURE		NTC 4321 - 4 ISO 10545 - 4	Mínimo 35 N/mm ² / Minimum 35 N/mm ²	Mínimo 35 N/mm ² / Minimum 35 N/mm ²
RESISTENCIA A LA ABRASIÓN ABRASION RESISTANCE		NTC 4321 - 7 ISO 10545 - 7	Informe de cumplimiento de la clase de abrasión y los ciclos	Clase 4 / Class 4
COEFICIENTE DE FRICCIÓN DINÁMICO DYNAMIC COEFFICIENT OF FRICTION		NTC 4321 - 17 ISO 10545 - 17	Declarado por el fabricante / Metodo de ensayo disponible	Clase 2 / Class 2
RESISTENCIA AL MANCHADO RESISTANCE TO STAINING		NTC 4321 - 14 NTC 4321 - 14	Mínimo clase 3 / Minimum class 3	Mínimo clase 4 / Minimum class 4
RESISTENCIA A AGENTES QUÍMICOS RESISTANCE TO CHEMICALS		NTC 4321 - 13 NTC 4321-2 - 13	Mínimo clase B / Minimum B class	Mínimo Clase A / Minimum A Class
RESISTENCIA AL CHOQUE TÉRMICO THERMAL SHOCK RESISTANCE		NTC 4321-2 - 9 NTC 4321 - 9	La indicada por el fabricante/Manufacturer to state classification	Mínimo clase BA / Minimum BA class